



DOW™ LDPE 722

The Dow Chemical Company - Low Density Polyethylene Resin

Tuesday, April 9, 2019

General Information

Product Description

Dow™ LDPE 722 is used in flexible packaging and paperboard coating applications such as liquid/juice, laminate tube, condiment pouches, dry foods packaging, snack foods packaging, moist foods packaging, sugar pouches, lidding stock and medical packaging. DOW LDPE extrusion coating resins provide optimal neck-in and draw-down performance with minimal taste/odor contribution.

DOW Polyethylene 722 is a broad molecular weight distribution homopolymer designed to offer good impact strength and crack resistance, with excellent flexibility. The resin has good processability over a wide range of molding conditions.

- Typical applications include caps/closures
- Good impact, ESCR with excellent flexibility

Complies with:

- CANADIAN HPFB NO OBJECTION (WITH LIMITATIONS)
- EU, No 10/2011
- U.S. FDA 21 CFR 177.1520 (c) 2.2
- U.S. FDA DMF

Consult the regulations for complete details.

General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Latin America	• North America
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• DMF Unspecified Rating • EU No 10/2011	• FDA 21 CFR 177.1520(c) 2.2 • HPFB (Canada) No Objection ¹	
Forms	• Pellets		
Processing Method	• Extrusion Coating	• Injection Molding	

ASTM & ISO Properties²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.920	0.920	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) ³			ASTM D1693
122°F (50°C), 100% Igepal, F50	< 1.00 hr	< 1.00 hr	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³			ASTM D638
Yield	1200 psi	8.27 MPa	
Break	1400 psi	9.65 MPa	
Tensile Elongation ³			ASTM D638
Yield	4.0 %	4.0 %	
Break	500 %	500 %	
Flexural Modulus - 2% Secant ³	34000 psi	234 MPa	ASTM D790B
Coefficient of Friction	0.60	0.60	ASTM D1894

Copyright ©, 2019 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

DOW™ LDPE 722

The Dow Chemical Company - Low Density Polyethylene Resin

Films	Typical Value (English)	Typical Value (SI)	Test Method
Seal Initiation Temperature ⁴	221 °F	105 °C	Internal Method
Water Vapor Transmission Rate	1.7 g·mil/100in ² /atm/24 hr	0.67 g·mm/m ² /atm/24 hr	ASTM F1249
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Impact Strength ^{5, 3}	130 ft·lb/in ²	273 kJ/m ²	ASTM D1822
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness ³ (Shore D)	43	43	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load ³ 66 psi (0.45 MPa), Unannealed	99.0 °F	37.2 °C	ASTM D648
Brittleness Temperature ³	-76.0 °F	-60.0 °C	ASTM D746
Vicat Softening Temperature	190 °F	87.8 °C	ASTM D1525
Melting Temperature (DSC)	224 °F	107 °C	Internal Method
Peak Crystallization Temperature (DSC)	204 °F	95.6 °C	Internal Method
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Melt Temperature - Recommended	600 to 630 °F	316 to 332 °C	Internal Method

Fabrication Conditions For Extrusion Coating Film:

- Screw Size: 3.5 in. (89 mm); 30:1 L/D
- Screw Type: Single Flight with Maddock Mixer
- Die Gap: 20 mil (0.508 mm)
- Melt Temperature: 625°F (329°C)
- Output: 250 lb/hr
- Screw Speed: 90 rpm

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)	Test Method
Maximum Line Speed	25.0 ft/sec	7.6 m/sec	Internal Method
Minimum Coating Thickness	0.30 mil	7.6 μm	Internal Method
Minimum Coating Weight	4.4 lb/ream	7.2 g/m ²	Internal Method
Neck-in (610°F (321°C), 1.0 mil (25.4 μm))	2.0 in	50.8 mm	Internal Method

Notes

¹ With limitations

² Typical properties: these are not to be construed as specifications.

³ Molded and tested in accordance with ASTM D4976.

⁴ Temperature at which 1 lb/in (4.4 N/25.4 mm) heat seal strength is achieved.
Heat Seal Strengths, Topware HT Tester 0.5 S dwell, 40 psi bar pressure, pull speed 250 mm/sec.

⁵ Type S